


BUTYLEN-AS39 P

Product information



Special advantages:



For temperatures up to +85 °C (+185 °F).



Fulfills EN 12068-C50 and DIN 30672-C50.



Fulfills ISO 21809-3, Type 12A-1.



Real co-extruded 3-ply tape.



Easy processing through adaptable and highly tear-resistant carrier film.



Compatible with factory coatings made of PE, PP, FBE, PU, CTE and bitumen.

Single tape system for the corrosion prevention coating of metal pipes and pipelines in accordance with DIN 30672, EN 12068, ASTM and AWWA. Corrosion prevention system proven for decades – for high mechanical and corrosive stresses.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-AS39 P is a cold applied single tape system for the corrosion prevention of metal pipes and pipelines in a high mechanical and corrosive stress classes.

With its outstanding properties, BUTYLEN-AS39 P is the proven corrosion prevention technology for cold applied corrosion prevention tapes since 1972. Due to the innovative formula, the tapes grow completely together in the overlapping area and create a long-lasting hose-type coating.

BUTYLEN-AS39 P is basically impermeable for water vapor and oxygen and it is resistant against soil bacteria and electrolytes.

BUTYLEN-AS39 P is compatible with factory coatings made of PE, PP, FBE, PU, CTE and Bitumen.

The system BUTYLEN-AS39 P consists of:

BUTYLEN-HT Primer

A solvent containing primer in accordance with EN 12068 and DIN 30672 for the corrosion prevention with **BUTYLEN** tapes. Please refer to the separate product information of the BUTYLEN-HT Primer.

BUTYLEN-AS39 P

A real co-extruded 3-ply plastic tape made from stabilized polyethylene carrier materials with butyl rubber adhesive.


BUTYLEN-AS39 P has a thickness of ≥ 0.8 mm.

BUTYLEN-AS39 P fulfills the international standards DIN 30672 and EN 12068.

Supplementary products:

BUTYLEN-W and **-WP Mastic** as permanently plastic formable butyl rubber mastic for the equalization of unevennesses and cavities.

DEPROTEC®-DRM PP rockshields made of polypropylene non-woven material for the additional mechanical protection of **BUTYLEN** coatings with shock absorbing and load distributing effects.



Typical product properties

Property	Unit	BUTYLEN-AS39 P Typical value	Test method
Carrier film color	-	Black	-
Butyl adhesive color inside	-	Grey	-
Butyl adhesive color outside	-	Black or yellow	-
Total thickness	mm	≥ 0.8	ISO 4591 ASTM D1000
Carrier film thickness app.	mm	≥ 0.28	
Inside adhesive layer thickness app.	mm	≥ 0.44	
Outside adhesive layer thickness app.	mm	≥ 0.08	
Elongation at break	%	≥ 600	DIN 30672
Tape strength	+23°C (+73.4°F) N/cm	≥ 100	EN 12068
Dielectric strength	kV / mm	≥ 40	DIN 53481
Water absorption	+23°C (+73.4°F) 1 day / 30 days %	≤ 0.1 / ≤ 0.4	DIN 53495 ASTM D570
Brittleness temperature	°C (°F)	-46±4 (-50.8±7.2)	DIN 53372
		-58±4 (-72.4±7.2)	GOST 10354

BUTYLEN-AS39 P (4 layers) with BUTYLEN-HT Primer

Property	Unit	Typical value		Required value	Test method
Electrical insulation resistance	Ohm m ²	≥ 10 ¹⁰		≥ 10 ⁸	EN 12068
Contact resistance	Ohm cm	≥ 10 ¹⁵		Not stated	DIN 53482 ASTM D257
Peel resistance metal/prime coat/AS39 P	N/cm	+23°C (+73.4°F)	+50°C (+122°F)	≥ 10 ≥ 1	EN 12068 ASTM D1000
		≥ 25	≥ 2.5		
Peel resistance layer to layer AS39 P / AS39 P	N/cm	+23°C (+73.4°F)	+50°C (+122°F)	≥ 10 ≥ 2	EN 12068
		≥ 33	≥ 2.5		
Indentation resistance - residual layer thickness at stamp load: (Stamp-Ø 1.80 mm – four-layer)	mm/N/mm ²	+50°C (+122°F)		> 0.6	EN 12068
		≥ 0.8 / 10 (fulfills class C)			
Impact resistance (4 layer)	J	≥ 15 (class C)		≥ 15	EN 12068
Cathodic disbondment resistance	mm	≤ 6		Not stated	ASTM G8
Lap shear strength	N/cm ²	+23°C (+73.4°F)		≥ 5	EN 12068
		on steel			
		on factory coating			
		≥ 15		≥ 5	

BUTYLEN tapes can be easily applied manually. The processing with the original **DEKOMAT**[®] wrapping devices is even more efficient. For **BUTYLEN** tapes with widths of > 50 mm, we recommend the use of the **DEKOMAT**[®] wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

BUTYLEN-AS39 P, Core Ø 78 mm

Tape width (mm)	Tape length (m)	Tape area (m ² /roll)	Content per box			App. Weight (kg)
			Number of rolls	Total tape area (m ²)	Total tape length (m)	
100	70	7	3	21	210	19,0
150	70	10,5	2	21	140	19,0

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-AS39 P** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@dekotec.com
www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.